



H O L Z
C E R T
A U S T R I A

CERTIFICATE OF FACTORY PRODUCTION CONTROL

1359 - CPD - 0034

In compliance with the Directive 89/106/EEC of the Council of European Communities of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to the construction products (Construction Products Directive - CPD), amended by the Directive 93/68/EEC of the Council of European Communities of 22 July 1993, it has been stated that the construction product

Strength graded structural timber with rectangular cross section

corresponding to the product specification listed on the back side

produced by the manufacturer

Schaffer Sägewerk-Holzexport GmbH
Hintersieding 12
A-8741 Eppenstein

in the factory

A-8741 Eppenstein, Hintersieding 12

is submitted by the manufacturer to the initial type-testing of the product and a factory production control and that the approved body – HOLZFORSCHUNG AUSTRIA - has performed the initial inspection of the factory and of the factory production control and performs the continuous surveillance, assessment and approval of the factory production control.

This certificate attests that all provisions concerning the attestation of factory production control described in Annex ZA of the standard

EN 14081-1:2005

were applied.

This certificate was first issued on 19.12.2007 and remains valid as long as the conditions laid down in the harmonised technical specification in reference or the manufacturing conditions in the factory or the FPC itself are not modified significantly.

Vienna, 19.12.2007

HOLZCERT AUSTRIA


DI M. Spatt
Authorised signatory




DI S. Czamutjian
Head of Certification Body

Product specification
to the EC-CERTIFICATE 1359 - CPD – 0034
dated 19.12.2007

Construction product:

Strength graded structural timber with rectangular cross section
(buildings and bridges)

Wood species:	Picea abies - Spruce Abies alba - Fir Larix decidua - Larch
Origin:	MNO
Visual grading:	ÖN DIN 4074-1
Strength classes ref. EN 338:	C16, C24, C30
Grading classes ref. DIN 4074-1:	S7, S10, S13
Reaction to fire:	D-s2, d0
Natural durability:	Picea abies - Spruce 4 Abies alba - Fir 4 Larix decidua - Larch 3 - 4

